

Test Report

Report No.: FLSHF000101720002

Page 1 of 3

Applicant : Maanshan Tong-Jie-Liang Biomaterials Co.,Ltd

Address : No.2196 HongQiNanLu , Maanshan economic and technological development zone

Report on the submitted sample(s) said to be:

Sample Name : PLA SPUNLACE NONWOVEN FABRIC FOR SANITARY

Model No. : TJL-N30605

Manufacturer : Maanshan Tong-Jie-Liang Biomaterials Co.,Ltd

Sample Quantity : 50g

Sample Status : Solid

Sample Received Date : Jun.05, 2013

Sample Tested Date : Jun.05, 2013- Jun.21, 2013

Test Requested: As specified by client, in accordance with GB/T 20944.3-2008 Textiles
-Evaluation for antibacterial activity Part 3:Shake flask method

Test Component(s): PLA SPUNLACE NONWOVEN FABRIC FOR SANITARY

Test Item(s) : Please refer to the following page(s).

Test Method: Please refer to the following page(s).

Test Result(s): Please refer to the following page(s).

Tested by

Ji Han

Reviewed by

Amos Zhu

Approved by

Jiaming Zhou

Date

Jun.21, 2013

Jiaming Zhou

Technical manager

Centre Testing International (Shenzhen) Corporation, Shanghai Branch

No. 1996, Xinqiniao Road, Pudong, Shanghai



Test Report

Report No.: FLSHF000101720002

Page 2 of 3

Test Method:

With reference to GB/T 20944.3-2008 Textiles-Evaluation for antibacterial activity-Part 3: Shake flask method.

Test Organisms:

Staphylococcus aureus (ATCC 6538)

Escherichia coliform (ATCC 8739)

Candida albicans (ATCC 10231)

Test Result:

1. Test effectiveness:

For *Staphylococcus aureus* and *Escherichia coliform*, when the value of microorganism growth ≥ 1.5 ; for *Candida albicans*, when the value of microorganism growth ≥ 0.7 , and the concentration of microorganisms in reference flask after inoculation increased, the testing is effective. Otherwise, the testing must be conducted again.

$$F = \lg W_t - \lg W_0$$

W_t - the value of microorganism growth on controlled sample;

W_t - the average value of microorganisms after inoculation and vibrating 18 hours on 3 controlled samples;

W_0 - the average value of microorganisms after inoculation immediately on 3 controlled samples;

2. Calculation for bacteriostatic rate:

$$\text{Bacteriostatic rate} = (W_t - Q_t) / W_t \times 100\%$$

Q_t - the average value of microorganisms after inoculation and vibrating 18 hours on 3 test samples.

3. Result:

Test Organisms	Inoculation concentration (CFU/ml)	W_0 (CFU/ml)	W_t (CFU/ml)	Q_t (CFU/ml)	F	Bacteriostatic rate (%)
<i>Staphylococcus aureus</i>	3.6×10^5	2.4×10^4	1.3×10^6	6.0×10^4	1.7	95
<i>Escherichia coliform</i>	3.6×10^5	2.4×10^4	1.5×10^6	7.1×10^4	1.8	95
<i>Candida albicans</i>	2.6×10^5	1.8×10^4	1.5×10^5	4.8×10^3	0.9	92

Evaluation for antibacterial activity:

When bacteriostatic rate to *Staphylococcus aureus* and *Escherichia coliform* is not less than 70%, or bacteriostatic rate to *Candida albicans* is not less than 60%, the antibacterial activity for sample submitted is acceptable.

Test Report

Report No.: FLSHF000101720002

Page 3 of 3

Photo(s) of the sample(s)



*** End of report ***

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of CTI, this report can't be reproduced except in full, as well as can't be propagated improperly by using the testing results arbitrarily.